

**Marktegs AB**  
**TECHNICAL DATA SHEET**  
**GEO TEXTILE NETTING ( 740 GSM )**

|   |  |
|---|--|
| <b>Product Material</b>                     | 100% Coir Fibre  |
|   | Fibre is Spinned in to coir yarn and a net is produced |
| <b>Origin</b>                               | Sri Lanka  |
| <b>Colour</b>                               | Natural Brown  |
| <b>Warp &amp; Weft</b>                      | Number of Weft Threads - 40- 35                        |
| <b>Weight of the Net</b>                    | 740g/ m, +/- 5%  |
| <b>Tensile Strength dry</b>                 | MD approx. 18,2 kN/m                                   |
|   | CD approx. 12,4 kN/m                                   |
| <b>Elongation at the breaking point dry</b> | MD 29,3 %  |
|   | CD 29,8%   |
| <b>Weight of Roll</b>                       | 74 kgs +/- 3%  |
| <b>Volume of a Roll</b>                     | 0.5 cbm  |
| <b>Customs Traiff No</b>                    | 53 11 00 90  |

Please note that the above figures are based on average values. The above specifications may vary due to natural variations on coir fiber.